

# PRODUCT DATASHEET

## Meta-Braze™ BM 41 Flux Paste

Meta-Braze™ BM41 Flux Paste is a brown coloured, boron-modified flux paste specifically designed for silver brazing of tungsten carbide and PCD. The boron addition helps to improve wetting of the braze alloy onto difficult-to-wet parent materials such as tungsten carbide. This flux can also be used for brazing of cast iron.

Meta-Braze™ BM41 Flux Paste is a highly active flux with good fluidity and a medium life span.

### Product Details

Composition:	Proprietary
Specification / Standard:	EN 1045:1997: FH12 / ISO 18496:2021 FH12 B
Active Range:	550-800°C

### Conditions For Use

First remove surface contamination from the parts to be brazed. They should be free from oil and grease; surface oxide should be mechanically removed. Stir Meta-Braze™ BM 41 Flux Paste before use.

A layer of flux paste should be applied, using a paint brush, to the joint surfaces before assembly of the parts. Further flux should then be applied externally either side of the joint mouth and onto any braze preforms placed outside the joint. Next the parts should be heated evenly to the brazing temperature, without localised overheating. During heating the flux will bubble as water is boiled off and the flux will provide a smooth brown covering as the brazing temperature is reached. If the flux becomes burnt and blackened it indicates overheating or inadequate fluxing.

The flux residues of this product, left after completion of the brazing operation, are corrosive and should be removed. For best results soak the components in warm water (60°C) for approximately 30 minutes then brush residues off and rinse before drying.

Store flux at ambient room temperature with the lid on.

### Forms of Supply

1kg Pots

Vacuum Brazing Consultants Limited t/a VBC Group cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products will be used. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is given in good faith, being based on the latest information available to VBC Group and is, to the best of VBC Group's knowledge and belief, accurate and reliable at the time of preparation. However, no representation, warranty or guarantee is made as to the accuracy or completeness of the information and VBC Group assumes no responsibility therefore and disclaims any liability for any loss, damage or injury howsoever arising (including in respect of any claim brought by any third party) incurred using this information. The product is supplied on the condition that the user accepts responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent or any other proprietary rights of any third party must not be assumed.