

PRODUCT DATASHEET

Meta-Braze™ HT 21 Flux Paste

Meta-Braze™ HT21 Flux Paste is a high temperature flux that is designed for use with copper-based brazing alloys such as Meta-Braze™ Cu 058, 052, 067. It can be used to join mild and low alloy steels and tungsten carbide with brazing filler metals melting between 750-1150°C. Typical applications are in the brazing of tools for construction, mining, agriculture and oil and gas drilling. It may also be used in conjunction with copper based infiltrant materials.

Product Details

Composition:	Proprietary
Specification / Standard:	EN 1045:1997: FH21 / ISO 18496:2021 FH21
Active Range:	750-1200°C

Conditions For Use

This paste should be brushed onto the joint surfaces before assembly. Further flux should then be applied externally either side of the joint opening.

The flux residues of this product, left after completion of the brazing operation, are corrosive and should be removed. They are very hard and insoluble in water and must be removed by mechanical methods such as grit blasting or grinding.

Forms of Supply

Pots 900gm, other sizes on request

Vacuum Brazing Consultants Limited t/a VBC Group cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products will be used. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is given in good faith, being based on the latest information available to VBC Group and is, to the best of VBC Group's knowledge and belief, accurate and reliable at the time of preparation. However, no representation, warranty or guarantee is made as to the accuracy or completeness of the information and VBC Group assumes no responsibility therefore and disclaims any liability for any loss, damage or injury howsoever arising (including in respect of any claim brought by any third party) incurred using this information. The product is supplied on the condition that the user accepts responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent or any other proprietary rights of any third party must not be assumed.