

Solda-Met™ 60L

Tin-Lead Soft Solder

Solda-Met™60L has a short melting range, is relatively free flowing and is widely used in soldering copper and copper based alloys.

Standard	ISO 9453:2014	Alloy No. 103
Melting Range	183°C - 190°C	
Chemical Composition	Tin Lead	60% 40%
Conditions for Use	For use with a separate flux, Solda-Met 1C, 2C, 3C or with a flux core	
Physical Properties	Density - 8.5 g/cm ³	
Forms of Supply	Available as solid wire or with a flux core of either rosin or acid fluxes	

